EJOT MAXXtip®

Thread forming solutions for (ultra) high strength materials

EJOT MAXXtip® combines a carbo-austempered shank with an ultra hard screw tip. This unique combination allows completely new options for direct fastening into (ultra) high strength materials.

Due to the carbo-austempered microstructure (strength similar to 10.9) in the load-bearing area MAXXtip® screws are insensitive to hydrogen embrittlement. Therefore, galvanic surfaces can be applied without tempering leading to a thread flank hardness of at least 750 HV* in the forming area.

*In case of Zn flake surfaces, baking leads to a reduced thread flank. hardness in the forming area of at least 600 HV.



Heat treatment comparison of a case hardened screw and a MAXXtip® screw



EJOT. Bringing it together.

Main application fields of EJOT MAXXtip®:

> (Ultra) high strength steel sheets (at least UTS of 1200 MPa) using the thread types
  - SHEETtracs® up to 2 mm
  - Spiralform® analogous DIN 7500
> Cast iron (GJS und GJL) using the Spiralform® thread type

MAXXtip Spiralform®



MAXXtip SHEETtracs®



Application vs. material strengths

Material	Yield strength (MPA)	Tensile strength (MPa)	Hardening process	
			case-hardened	MAXXtip®
S 420MC	420	550	●	●
S 500MC	500	640	–	●
DP 800	620	800	–	●
CP-W 800	680	800	–	●
S 700MC	700	850	–	●
DP1000	700	1000	–	●
CP900Y1180T-CP	900	1180	–	●
MSW 1200	900	1200	–	●



Application example for high strength sheets

The advantages of MAXXtip® become obvious when fastening plastic seat attachment parts to seat frames made of S700MC. Even in (ultra) high strength sheets safe and reliable direct fastening can be achieved. This results in a significant reduction of working operations and costs.

Application example for cast iron

In case to cast iron (GJL or GJS) thread cutting can be omitted if MAXXtip® screws are used. Application fields can be found in the complete motor vehicle powertrain as well as in pumps, compressors or electric engines. A direct fastening into boreholes or cast holes is possible without any further preparations.

Construction hints



Screw length MAXXtip®	$L > s_1 + s_2 + L_{inductive}$



Screw length MAXXtip®	$L > s_1 + 1{,}5 \times d + L_{inductive}$

Further information at www.ejot.com/industry or please contact
Jonas Weber: Tel.: +49 2751 529 2171, E-Mail: jonas.weber@ejot.com

EJOT SE & Co. KG · **Market Unit Industry** · Im Herrengarten 1 · 57319 Bad Berleburg · Germany
T +49 2751 529-0 · F +49 2751 529-559 · industrie@ejot.com · www.ejot.de/industrie

EJOT. Bringing it together.

07.26/PDF 07.26 Technische Änderungen vorbehalten.